



No. 2603418  
 Levitex (xinxiang) co ltd, weiqi rd, Xinxiang, Henan, China  
 E-mail:Info@levitex.com  
 www.levitex.com



Flame Retardant 100% Cotton Fabric

Fabric Description	TEST METHOD	PERFORMANCE		
Fiber content		100% Cotton		
Weave		Satin		
Weight	ISO 3801:1977	460 GSM		
Width	ISO 22198:2006	150 CM		
<b>Physical Properties</b>				
Shrinkage warp wash 5×60°	ISO 5077:2007	≤ 3%		
Shrinkage weft wash 5×60°	ISO 5077:2007	≤ 3%		
Tensile strength warp	ISO 13934-1:2003	1800 N		
Tensile strength weft	ISO 13934-1:2003	950 N		
Tear strength warp	ISO 13937-1:2000	60 N		
Tear strength weft	ISO 13937-1:2000	60 N		
<b>Color Fastness</b>		<b>Light</b>	<b>Middle</b>	<b>Dark</b>
Colorfastness to wash 60°	ISO 105-C06:2010	4	4	4
Colorfastness to water	ISO 105-E01:2013	4	4	4
Colorfastness to rubbing dry	ISO 105-X12:2016	4	4	3/4
Colorfastness to rubbing wet	ISO 105-X12:2016	3-4	3-4	2/3
<b>Functional</b>				
	ISO15025:2016			
Flame Retardant	After Flame	<2		
	After Glow	<2		
	Carbon Length	<100MM		
Flame Retardant (After 50 washes)	After Flame	<2		
	After Glow	<2		
	Carbon Length	<100MM		
<b>Chemical Properties</b>				
PH of aqueous extract	ISO 3071:2020	4-7.5		
Washing Symbols				